

BITOLA (pol.)	BITOLA(mm)	REDONDAS(kg/m)	QUADRADAS (kg/m)	SEXTAVADA(kg/M)
1/8	3,18	0,06	0,08	0,07
3/16	4,76	0,14	0,18	0,15
5/16	7,94	0,39	0,49	0,43
3/8	9,53	0,56	0,71	0,62
7/16	11,11	0,76	0,97	0,84
1/2	12,7	0,99	1,27	1,1
9/16	14,29	1,26	1,6	1,39
5/8	15,87	1,55	1,98	1,71
11/16	17,46	1,88	2,39	2,07
3/4	19,05	2,24	2,85	2,47
13/16	20,64	2,62	3,34	2,9
7/8/	22,22	3,04	3,88	3,36
15/16	23,81	3,49	4,45	3,86
1	25,4	3,97	5,06	4,39
1/1	26,99	4,49	5,72	4,95
1/1	28,57	5,03	6,41	5,55
1/3	30,16	5,6	7,14	6,19
1/1	31,75	6,21	7,91	6,85
1/3	34,93	7,52	9,58	8,3
1/1	38,1	8,94	11,4	9,87
1/5	41,27	10,49	13,37	11,58
1/3	44,45	12,17	15,51	13,44
1/7	47,62	13,97	17,8	15,42
2	50,8	15,9	20,26	17,55
2/1	53,97	17,94	22,87	–
2/1	57,15	20,12	25,64	–



BITOLA (pol.)	BITOLA(mm)	REDONDAS(kg/m)	QUADRADAS (kg/m)	SEXTAVADA(kg/M)
2/3	60,33	22,42	28,57	—
2/1	63,5	24,84	31,65	—
2/5	66,67	27,38	34,89	—
2/3	69,85	30,05	38,3	—
2/7	73,02	32,84	41,86	—
3	76,2	35,77	45,58	—
3/1	79,37	38,81	49,45	—
3/1	82,55	41,98	53,49	—
3/3	85,73	45,27	57,69	—
3/1	88,9	48,68	62,04	—
3/5	92,07	52,22	66,54	—
3/3	95,25	55,89	71,22	—
3/7	98,42	59,67	76,04	—
4	101,6	63,59	81,03	—
4/1	104,77	67,62	86,17	—
4/1	107,95	71,78	91,48	—
4/3	111,13	76,08	96,95	—
4/1	114,3	80,48	102,56	—
4/5	117,47	85	108,32	—
4/3	120,65	89,67	114,27	—
4/7	123,82	94,44	120,35	—
5	127	99,35	126,61	—
5/1	130,17	104,38	133,01	—
5/1	133,35	109,54	139,59	—
5/3	136,53	114,83	146,33	—
5/1	139,7	120,22	153,2	—



BITOLA (pol.)	BITOLA(mm)	REDONDAS(kg/m)	QUADRADAS (kg/m)	SEXTAVADA(kg/M)
5/5	142,87	125,74	160,23	—
5/3	146,05	131,4	167,45	—
5/7	149,22	137,16	174,79	—
6	152,4	143,07	182,32	—
6/1	155,57	149,08	189,99	—
6/1	158,75	155,24	197,83	—
6/3	161,93	161,52	205,84	—
6/1	165,1	167,91	213,98	—
6/5	168,27	174,42	222,27	—
6/3	171,45	181,07	230,75	—
6/7	174,62	187,83	239,36	—
7	177,8	194,74	248,16	—
7/1	180,97	201,74	257,09	—
7/1	184,15	208,89	266,2	—
7/3	187,33	216,17	275,48	—
7/1	190,5	223,55	284,88	—
7/5	193,67	231,05	294,44	—
7/3	196,85	238,7	304,19	—
7/7	200,02	246,45	314,06	—
8	203,2	254,35	324,13	—
8/1	209,55	270,49	344,7	—
8/1	215,9	287,13	365,91	—
8/3	222,25	304,27	387,75	—
9	228,6	321,91	410,22	—
9/1	234,95	340,04	433,33	—
9/1	241,3	358,67	457,07	—



BITOLA (pol.)	BITOLA(mm)	REDONDAS(kg/m)	QUADRADAS (kg/m)	SEXTAVADA(kg/M)
9/3	247,65	377,8	481,44	—
10	254	397,42	506,45	—
10/1	266,7	438,15	558,36	—
11	279,4	480,88	612,81	—
11/1	292,1	525,59	669,78	—
12	304,8	572,28	729,29	—
12/1	317,5	620,97	791,33	—
13	330,2	671,64	855,9	—
14	355,6	778,94	992,64	—
15	381	894,19	1139,51	—
16	406,4	1017,39	1296,51	—
17	431,8	1148,54	1463,64	—
18	457,2	1287,64	1640,9	—
19	482,6	1434,68	1828,29	—
20	508	1589,67	2025,8	—